

## TEST REPORT

No. : XMIN2505001066CM01\_EN

Date : 2025-05-23

Page: 1 of 3



CUSTOMER NAME: CHIPING CONCEPT STEP TRADE CO., LTD.  
ADDRESS: ZHOUSHUANG VILLAGE XINFU STREET OFFICE, CHIPING  
COUNTY, LIAOCHENG CITY, SHANDONG PROVINCE, CHINA

Sample Name : laminate floor  
Other Information : Importer: Floor Fort (Флор Форт)

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

\*\*\*\*\*

Date of Receipt : 2025-05-16  
Testing Period : 2025-05-16 ~ 2025-05-23  
Test result(s) : For further details, please refer to the following page(s)  
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for  
SGS-CSTC Standards Technical  
Services Co.,Ltd. Xiamen Branch.

Bryan Hong  
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: [CN.Doccheck@sgs.com](mailto:CN.Doccheck@sgs.com)

SGS-CSTC Standards Technical Services Co., Ltd.  
Xiamen Branch Testing Laboratory

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China 361101  
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编: 361101

t (86-592) 5765857 www.sgsgroup.com.cn  
t (86-592) 5765857 sgs.china@sgs.com

## TEST REPORT

No. : XMIN2505001066CM01\_EN


Date : 2025-05-23

Page: 2 of 3

### Summary of Results:

No.	Test Item	Test Method	Result
1	Abrasive Resistance	EN 13329:2023 & ISO 24338:2022 Method A	Average abrasion cycles: 6200 revolutions (Not worn out to the substrate) Abrasion class: AC5

### Original Sample Photo:



## TEST REPORT

No. : XMIN2505001066CM01\_EN

Date : 2025-05-23

Page: 3 of 3

Test Item: Abrasive Resistance

Sample Description: See photo

Test Method: EN 13329:2023 & ISO 24338:2022 Method A

Test Condition:

Specimen: 100mm×100mm, 3pcs

Type of wheel: CS-0

Load: 5.4N/wheel

Rotating speed: 60r/min

Abrasive paper strips: S-42(P180)

Lab Environmental Condition: (23±2)°C, (50±5)%RH

Test Result:

Average abrasion cycles: 6200 revolutions (Not worn out to the substrate)

Abrasion class: AC5

Note: Abrasion class according to EN 13329:2023 Table 2 as follow:

Abrasion class	AC1	AC2	AC3	AC4	AC5	AC6
Average abrasion cycles	≥500	≥1000	≥2000	≥4000	≥6000	>8500

\*\*\*\*\*End of report\*\*\*\*\*